


UNIQ[®] FOAM 152 S

Silicone free polymer defoamer



UNIQ[®] FOAM 152 S is a strong silicone free defoamer can be used for all solvent borne coating systems, especially suitable for solvent free self-leveling epoxy system. The additive has excellent defoaming and strong de-aeration, and not influence on the intercoat adhesion. At the same time, it will improve the leveling properties and give excellent film appearance in high gloss systems and will give good compatibility.

Special Features

- Quick de-aeration and defoaming effect for pigmented solvent free epoxy system
- Does not interfere intercoat adhesion
- Excellent film appearances
- Silicone-free
- Heat stable

Application

Architectural coatings	<input type="checkbox"/>
Wood and furniture coatings	<input checked="" type="checkbox"/>
Automotive and refinish coatings	<input type="checkbox"/>
Can/coil coatings	<input type="checkbox"/>
Protective coatings	<input checked="" type="checkbox"/>
Industrial coatings	<input checked="" type="checkbox"/>

highly recommended
recommended

Product Specification

Solvent	PMA / Hydrocarbons
Density 20°C	C9 aromatics
Refractive index	0.92 g/cm ³
Color	1.480
Appearance	Max. 1
	Slight hazy colorless liquid

Addition levels

- Based on total formulation: 0.1 – 1.0%

Added in grinding stage or under high shear forces incorporation.

Although the product may be slightly turbid, this cannot be observed anymore in the final dry film.

Packaging

- 22 kg
- 170 kg

Shelf life

UNIQ[®] FOAM 152 S should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture.

UNIQCHEM (UK) CO., LTD

www.uniqchem.com
Info@uniqchem.com

Regional headquarters

UNIQ[®]FOAM, UNIQ[®]FLOW, UNIQ[®]WET, UNIQ[®]SPERSE, UNIQ[®]LIGHT, UNIQ[®]COLOR, UNIQ[®]MICA, UNIQ[®]CURE, UNIQ[®]JET
This information is given to the best of our knowledge. Because of the multitude of formulations, production and application conditions, all the above mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This datasheets replaces all previous issues – Printed in UK

© Copyright UNIQCHEM (UK) CO., LTD.

Asia: UNIQCHEM Shanghai Co., Ltd.
EMEA: UNIQCHEM GmbH

Tel: +86 21 5433 6480
Tel: +49 5921 853 7428

asia@uniqchem.com
eu@uniqchem.com