



Regional Headquarters

Europe, Middle East and Africa UNIQCHEM GmbH

Hollandstrasse 7
D-48527 Nordhorn, Germany
Tel: +49 (0) 5921 853 7428
Email: eu@uniqchem.com

Asia Pacific UNIQCHEM Shanghai Co., Ltd.

1809 Qixin Road, West Zone, Building 8 Room 2308
Red Dot City ,Minhang District ,
201101 Shanghai , China
Tel: +86 (0) 21 5433 6480
Email: asia@uniqchem.com

Additives for General Industrial Coatings

This information and all further technical advice is based on our present knowledge and experience . However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, nowarranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or futher developments . The customer is not released from the obligation to product careful inspection and tsetting of incoming goods. Perfomãance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

UNIQ® FOAM Defoamers

Product	Silicone	Polymer / Non-silicone	Main solvent	Water based	Solvent based	Solvent free	Characteristic	Addition amount (%)	Emulsion alkyd	Water reducible systems	Hybrid	Emulsion	Thermo plastic acrylic	NC/Chlor. rubber	2-pack PU	2-pack Epoxy	Baking systems	Air drying alkyds	UV
UNIQ®FOAM 120 S		•	SPB 140-165		•		strong defoamer especially during production and application to avoid foam formation	0.1-1.0					••	••	••	•	••	••	•
UNIQ®FOAM 131 S		•			•		Defoamer for pigmented coatings and especially against microfoam and popping. Has leveling properties.	0.1-1.0					••	•	•••		•••		
UNIQ®FOAM 132 S		•	PMA		•		Defoamer for clear coatings and pigmented systems, especially against microfoam and popping in 2K PU systems. High clarity.	0.1-1.0					•••	••	•••		•	•	
UNIQ®FOAM 150 S		•			•	•	Solvent free version of 132S.	0.1-1.0							••	•	••		••
UNIQ®FOAM 152 S		•			•	•	Solvent free epoxy flooring, 2C PU systems and HS systems, good working against micro-foam	0.1-1.0							••	•••	••		•••
UNIQ®FOAM 180 W		•	Butyl glycol	•			Especially to avoid pinholing and popping reduce sensitivity for film thickness, often used in combination with other defoamer	0.3-3.0	•	•••	••	•••			••	••			
UNIQ®FOAM LP2507		•	-	•			Suited for pigment concentrates and paint systems, especially for 2C PU	0.1-1.0	••	•••	••	•••			•••	••			
UNIQ®FOAM 245 S	•		DIBK		•		Best defoamer for spraying, roller, brushing and curtain coating applications, good working for against micro and macro-foam	0.1-0.7					••	••	•••	•••	•	•••	
UNIQ®FOAM 272 S	•		PMA Alkylbenzene		•	•	Solvent free epoxy flooring, 2C PU systems and HS systems	0.1-1.0					•	•	••	•••	••		••
UNIQ®FOAM 280 W	•		—	•			All-round WB defoamer	0.1-1.0	••	•••	••	••			••	•			
UNIQ®FOAM 295 W	•		—	•	•	•	Especially suited for primers and topcoats with strong working against micro-foam	0.1-1.0	•••	•••	•••	•••			••	••			
UNIQ®FOAM LP2500	•		—	•			Strong defoamer for pigment paste preparations, also suited for topcoats	0.1-1.0	•••	•••	•••	•••			•••	•••			
UNIQ®FOAM LP2560	•		—	•			Strong defoamer with good compatibility, easy to use, suited for pigment and non pigmented systems	0.1-1.0	•••	•••	•••	•••			••	•••			

UNIQ® SPERSE Dispersing Agents

Product	Principal Component	Active (%)	Amine value mgKOH/g	Acid value mgKOH/g	Water based	Solvent based	Solvent free	Characteristic	Emulsion alkyd	Water reducible systems	Hybrid	Emulsion	Thermo plastic acrylic	NC/Chlor. rubber	2-pack polyurethane	2-pack Epoxy	Baking systems	Air drying alkyds	UV
UNIQ®SPERSE 510 S	PU Dispersant	52	6	14		•		Specially suited for TiO2, matting agents, fillers for primers and topcoats. Avoid sedimentation						••	•••	••	••	••	••
UNIQ®SPERSE 550 S	PU Dispersant	45	14	—		•		All-round dispersant agent for general purpose						•	••	•••	••	••	••
UNIQ®SPERSE 560 S	PU Dispersant	30	8	—		•		High performance dispersing agent for refinish/automotive. High transparency.						••	••	•••	••	•••	••
UNIQ®SPERSE 605 S	Polyester dispersant	40	19	8		•		Excellent dispersing agent for high jetness, high transparent pigment, automotive/refinsh and coil						•••	•••	•••	•••	•	•
UNIQ®SPERSE 650 U	Acrylic-polyester dispersant	100		14	•	•	•	Universal dispersing agent for Tio2, matting agents, fillers, suited for water-, solvent and solvent free systems	••	••	••	••	••	•	••	••	••	••	••
UNIQ®SPERSE 680 U	Acrylic-polyester dispersant	100	65	9	•	•	•	Dispersing agent for Carbon black and some red pigments. Can be post added to protect floating in system	••	•••	•••	•••	•••	•••	•••	••	•••	•	•••
UNIQ®SPERSE 690 W	Block dispersant	40	15	15	•			All-round dispersant agent for general purposefor water based systems. High transparency and performances	•••	•••	•••	•••			•••	•••			•••
UNIQ®SPERSE 710 S	Phosphoric dispersant	52	—	80		•		Dispersing agent for TiO2 and fillers. Gives very low viscosity						••	••	•••	••	••	•
UNIQ®SPERSE 730 U	Modified Acrylic Polymer	100	—	60	•	•	•	Excellent wetting and dispersing agents for TiO2 for high performance applications	•••	•••	•••	•••	•••	•••	••	••	•••	••	•••
UNIQ®SPERSE 765 S	Unsaturated Carboxylic acid	52	—	125		•		Anti-flooding and anti-floating agent. Can be post added						••	••	••	•••	•••	••
UNIQ®SPERSE 770 U	Unsaturated Carboxylic acid	100	80	—	•	•		Excellent cost effective wetting agent for all kind of pigments						••	••	••	••	••	

UNIQ® FLOW Wetting Agents And Surface Modifiers

Product	Silicone	Acrylic	Fluor modified polymer	Active (%)	Main solvent	Surface tension reduction	Water base	Solvent - free based	Addition amount (%)	Characteristic	Wettability	anti-crater	Benard cell	Improve leveling	Improve slip	Scratch prevention	Defoaming properties
UNIQ®FLOW 350 W			•	100	—	•••	•	•	0.1-0.5	Excellent wetting, defoaming, anti-crater and leveling performances	••	••		•••			••
UNIQ®FLOW 361 S			•	100	—	•••		•	0.01-0.5	Very good wetting, vertical leveling and anti-crater performances	•••	•••		•••			•
UNIQ®FLOW 372 S			•	70	s-Butanol	•	•	•	0.1-1.0	Standard leveling agent with in water based system good defoaming properties	••			••			•
UNIQ®FLOW 375 S			•	70	Xylene	•		•	0.5-1.0	Standard leveling agent, good wetting	•			••			•
UNIQ®FLOW 376 S			•	70	PMA	•		•	0.5-1.0	Improved version of 375S, faster leveling and excellent compatibility	••	•		••			•
UNIQ®FLOW 380 S		•		100	—	0		•	0.5-1.5	Cost effective standard leveling agent with good defoaming properties				••			••
UNIQ®FLOW 384 S		•		100	Alkyl Benzene	0		•	0.5-1.5	Leveling agent with strong micro defoaming properties				•			•••
UNIQ®FLOW 386 S		•		52	PMA	0		•	0.5-1.5	All-round fast leveling agent				•••			
UNIQ®FLOW 392 S		•		52	PMA	0		•	0.2-1.0	Anti-popping and anti-pinholing agent especially for PU systems				•			••
UNIQ®FLOW 415 S	•			15	Butyl acetate	•••		•	0.5-1.0	Silicone leveling agent with slip properties	••	•	•••	•••	•••	••	
UNIQ®FLOW 488 U	•			100	—	•••	•		0.1-1.0	Excelent wetting agent with very low foam stabilization	•••	•••		••			
UNIQ®FLOW 493 U	•			100	—	•••	•	•	0.05-0.3	Silicone leveling agent with very good slip	••	••	•••	•••	•••	•••	
UNIQ®FLOW 495 U	•			100	—	•••	•	•	0.05-0.3	Silicone leveling agent with excellent handfeeling, low foam	••	••	•••	•••	•••	•••	•

UNIQ® VIS Rheology Control Agents And Conductivity Agents

Product	Principal Component	Solid (%)	Main solvent	Water based	Solvent based	Characteristic	Addition amount (%)	Emulsion alkyd	Water reducible systems	Hybrid	Thermo plastic acrylic	Emulsion	NC/Chlorinated rubber	2-pack polyurethane	2-pack Epoxy	Baking systems	Air drying alkyds	UV
UNIQ®VIS 840 W		90	water	•		Humectant, protecting for drying out pigment pastes	3.0-10.0	•	◦	•	•			•	•			
UNIQ®VIS 880 S	Quartinary ammonium compound	54	iso-butanol		•	Conductivity agent	0.1-2.0					◦	◦	•	◦	•	◦	•

UNIQ® LIGHT Light Stabilizers

Product	Principal Component	Active (%)	Water based	Solvent based	Characteristic	Addition amount (%)	Emulsion alkyd	Water reducible systems	Hybrid	Emulsion	Thermo plastic acrylic	NC/Chlorinated rubber	2-pack polyurethane	2-pack Epoxy	Polyester/alkyd/acrylate	Air drying alkyds
UNIQ®LIGHT 923	HALS	100		•	Acid system HALS	0.5-2.0					•	◦	•	◦	•	◦
UNIQ®LIGHT 992	HALS	100	◦	•	Cost effective HALS	0.5-2.0	•	•	•	•	•	◦	•	◦	•	◦
UNIQ®LIGHT 930	Benzotriazole	100	◦	•	General purpose use Light Stabilizer	1.0-3.0	•	•	•	•	•	◦	•	◦	•	◦

